



**HAL**  
open science

## **17 O NMR evidence of free ionic clusters $Mn^{+} CO_3^{2-}$ in silicate glasses: Precursors for carbonate-silicate liquids immiscibility**

Yann Morizet, Pierre Florian, Michael Paris, Fabrice Gaillard

### ► To cite this version:

Yann Morizet, Pierre Florian, Michael Paris, Fabrice Gaillard. 17 O NMR evidence of free ionic clusters  $Mn^{+} CO_3^{2-}$  in silicate glasses: Precursors for carbonate-silicate liquids immiscibility. The American Mineralogist, 2017, 102 (7), pp.1561-1564. 10.2138/am-2017-6133 . insu-01579409

**HAL Id: insu-01579409**

**<https://insu.hal.science/insu-01579409v1>**

Submitted on 2 Oct 2017

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

1 **Revision 1**

2  **$^{17}\text{O}$  NMR evidence of Free Ionic clusters  $\text{M}^{\text{n}+} \cdot \text{CO}_3^{2-}$  in silicate glasses: Precursors for**  
3 **carbonate-silicate liquids immiscibility**

4 Yann Morizet<sup>1\*</sup>, Pierre Florian<sup>2</sup>, Michael Paris<sup>3</sup>, Fabrice Gaillard<sup>4</sup>

5 (1) Université de Nantes, Nantes Atlantique Universités, Laboratoire de Planétologie et  
6 Géodynamique de Nantes (LPG), UMR CNRS 6112, 2 rue de la Houssinière, 44322  
7 NANTES, France

8 (2) CNRS-CEMHTI Conditions Extrêmes et Matériaux: Haute Température et Irradiation,  
9 UPR 3079, 1D avenue de la Recherche Scientifique, 45071, Orléans, France

10 (3) Institut des Matériaux Jean Rouxel (IMN), Université de Nantes, UMR CNRS 6502, 2 rue  
11 de la Houssinière, BP32229, 44322 NANTES Cedex 3, France

12 (4) CNRS/INSU-Université d'Orléans – BRGM, UMR 7327, Institut des Sciences de la Terre  
13 d'Orléans, 1A rue de la Férollerie, 45071, Orléans, France

14

15 Corresponding author: Yann Morizet

16 Postal address:

17 Laboratoire de Planétologie et Géodynamique de Nantes (LPG Nantes), UMR-CNRS 6112,  
18 Université de Nantes.

19 2 rue de la Houssinière, 44322 Nantes Cedex (FRANCE)

20 phone: +33 (0) 2 5112 5491

21 fax: +33 (0) 2 5112 5268

22 \*E-mail: [yann.morizet@univ-nantes.fr](mailto:yann.morizet@univ-nantes.fr)

23 Abstract

24 Carbon dioxide is a ubiquitous component of low-silica melts such as kimberlites or  
25 melilitites. It is currently assumed that CO<sub>2</sub> molecules dissolving in low-silica melts as  
26 carbonate groups (CO<sub>3</sub><sup>2-</sup>) induce a strong polymerization of the silicate network; however, the  
27 exact molecular configuration of this dissolution mechanism is still debated.


28 Using <sup>17</sup>O MAS NMR spectroscopy, we have investigated the carbonate molecular  
29 environment in a series of synthesized low-silica (31-41 wt.% SiO<sub>2</sub>), CO<sub>2</sub>-bearing (from 2.9  
30 to 13.2 wt.% CO<sub>2</sub>) silicate glasses analogous to melilitites and kimberlites. With the selective  
31 {<sup>13</sup>C}- {<sup>27</sup>Al}- and {<sup>29</sup>Si}-<sup>17</sup>O J HMQC NMR method, we show that CO<sub>2</sub> dissolved in the  
32 studied low-silica glasses is totally disconnected from the silicate network, forming Free Ionic  
33 Clusters (FIC) M<sup>n+</sup>..CO<sub>3</sub><sup>2-</sup> with M<sup>n+</sup> a charge compensating cation.

34 The M<sup>n+</sup>..CO<sub>3</sub><sup>2-</sup> FIC are considered as precursors to immiscibility in between carbonate and  
35 silicate liquids. Observed in all studied compositions, we suggest that this immiscibility can  
36 be produced from moderately to strongly depolymerized silicate melt compositions.

37 INTRODUCTION

38 Providing constraints on the CO<sub>2</sub> dissolution mechanisms in depolymerized silicate melts  
39 contributes to our knowledge of kimberlite (Brooker et al. 2011; Russell et al. 2012), melilitite  
40 (Keller et al. 2006; Bosshard-Stadlin et al. 2014) and carbonatite genesis (Mitchell 2005),  
41 which are CO<sub>2</sub>-enriched magmas. Carbonate – silicate liquid immiscibility is thought to be  
42 one possible genetic mechanism for these peculiar magmatic systems (Brooker and  
43 Kjarsgaard, 2011; Guzmics et al. 2015); however, the exact modalities of this mechanism  
44 remain poorly constrained.

45 Early work on CO<sub>2</sub> dissolution in silicate melt (Mysen et al. 1976; Eggler 1978; Mysen and  
46 Virgo 1980; Spera and Bergman 1980) suggested that CO<sub>2</sub> plays the role of polymerizing  
47 agent of the silicate network structure according to the following reaction:



49 In this reaction, a CO<sub>2</sub> molecule scavenges available oxygen from a Q<sup>n</sup> (a SiO<sub>4</sub> tetrahedron  
50 unit with n bridging oxygen) unit to form a CO<sub>3</sub><sup>2-</sup> group charge compensated by a network-  
51 modifying cation (e.g. Ca<sup>2+</sup>). Raman spectroscopic studies (Mysen et al. 2011; Mysen 2012;  
52 Moussallam et al. 2016) suggested that Eq. 1 proceeds to the right upon CO<sub>2</sub> dissolution  
53 inducing a change in the proportion of the different oxygen species (i.e. Non-Bridging  
54 Oxygen NBO and Bridging Oxygen BO). However, the exact molecular configuration of the  
55 CO<sub>3</sub><sup>2-</sup> groups is not identified. Several dissolution mechanisms have been invoked for CO<sub>2</sub>  
56 molecules in silicate melts. It has been suggested that CO<sub>2</sub> can form network carbonates (T-  
57 CO<sub>3</sub><sup>2-</sup>-T with T = Si or Al) and NBO-CO<sub>3</sub><sup>2-</sup> where a CO<sub>2</sub> molecule connects to an available  
58 NBO of a tetrahedron (Brooker et al. 2001; Guillot and Sator 2011; Morizet et al. 2014). An  
59 additional CO<sub>2</sub>-dissolution mechanism has been proposed on the basis of molecular dynamic  
60 simulations (Xue and Kanzaki 2013; Vuilleumier et al. 2015) and also inferred from Raman  
61 spectroscopic studies (Mysen et al. 2011; Mysen 2012; Moussallam et al. 2016). In this  
62 mechanism the CO<sub>3</sub><sup>2-</sup> molecular groups are be present in the silicate network as Free Ionic  
63 Clusters M<sup>n+</sup>..CO<sub>3</sub><sup>2-</sup> where M<sup>n+</sup> is a charge balancing cation (i.e. alkali or alkaline-earth). Each  
64 type of CO<sub>2</sub>-dissolution mechanism is a strong function of the glass chemical composition  
65 (Brooker et al. 2001). For a given chemical composition, the melt physical and chemical  
66 properties will be strongly affected by the type of CO<sub>2</sub>-dissolution mechanism.

67 In the present work, we show direct proof of the M<sup>n+</sup>..CO<sub>3</sub><sup>2-</sup> FIC existence in low-silica  
68 depolymerized melts. Based on <sup>17</sup>O MAS NMR spectroscopy, we demonstrate that CO<sub>3</sub><sup>2-</sup>

69 molecular groups in low-silica melt are disconnected from the silicate network. Such a  
70 dissolution mechanism represents the precursor of the immiscibility process between a silicate  
71 melt and a carbonate melt.

## 72 EXPERIMENTAL METHOD

73 Several Fe-free glass compositions were investigated via  $^{17}\text{O}$  NMR spectroscopy. The studied  
74 compositions are depolymerized with  $\text{SiO}_2$  content ranging from 30 to 40 wt.% (Table 1) and  
75 a Non-Bridging Oxygen concentration per Tetrahedron (NBO/T) ratio of 1.2 to 3.2 calculated  
76 from the chemical composition obtained from Electron Probe Micro-Analyses (EPMA, see  
77 Table 1 and Supplementary material). Studied compositions are analogous to natural  
78 kimberlites (Kjarsgaard et al. 2009) and melilitites (Keller et al. 2006).

79 The starting material was weighed into Pt capsules, which were then sealed by arc-welding.  
80 Experiments were performed in piston-cylinder apparatus using  $\frac{3}{4}$  inch talc-Pyrex high-  
81 pressure assemblies between 0.5 and 1.5 GPa and at 1525°C. Details of the experimental  
82 syntheses are provided in the Supplementary material.

## 83 ANALYTICAL METHOD

84 Major elements and  $\text{CO}_2$  concentrations: EPMA and Raman spectroscopy

85 We performed micro-Raman analyses on a Jobin-Yvon LabRam 300 spectrometer equipped  
86 with an Innova 300-5W Argon ion laser from Coherent© operating at a wavelength of 514 nm  
87 to determine the  $\text{CO}_2$  content dissolved in silicate glasses using the protocol proposed by  
88 Morizet et al. (2013). A detailed description of the Raman analyses and the  $\text{CO}_2$   
89 determination from them is provided in Supplementary material.

90 NMR spectroscopy

91 All Solid State  $^{17}\text{O}$  NMR were conducted on a Bruker 850 MHz Avance III Wide Bore  
92 spectrometer operating at a frequency of 115.3 MHz and referenced against liquid  $\text{H}_2\text{O}$  at 0  
93 ppm. The  $^{17}\text{O}$  spectra were acquired using Full Hahn-echo and  $\{^{27}\text{Al}, ^{13}\text{C}, ^{29}\text{Si}\}$  J-HMQC  
94 (Heteronuclear Multiple-Quantum Correlation) pulse sequences (Amoureux et al. 2007;  
95 Keeler 2010). The details of the analytical conditions are given in the Supplementary material.  
96 The J-HMQC experiment uses the so-called scalar coupling (“J”) which arises from the  
97 electrons involved in the bond between two nuclei and allows the creation of Heteronuclear  
98 Multiple-Quantum Coherences. In an  $\{X\}$ - $^{17}\text{O}$  J-HMQC experiment where oxygen is the  
99 observed nuclei and X the indirect one, the resulting  $^{17}\text{O}$  spectrum displays only the oxygen  
100 environments that are chemically bound to X.

## 101 RESULTS AND DISCUSSION

102 The  $^{17}\text{O}$  MAS and  $\{X\}$ - $^{17}\text{O}$  J-HMQC NMR spectra are shown in Figure 1 for several samples:  
103 XE-2 (Figure 1A), HK-1 (Figure 1B), HK-M (Figure 1C) and RB8E-12 (Figure 1D). Several  
104 oxygen environments are witnessed in the  $^{17}\text{O}$  MAS NMR spectra:  $\sim+50$  ppm assigned to  $^{17}\text{O}$   
105 nuclei in BO configuration associated with Si or Al tetrahedra;  $\sim+100$  ppm assigned to  $^{17}\text{O}$   
106 nuclei in NBO configuration (Stebbins et al. 1999; Lee and Stebbins 2003; Kelsey et al. 2008)  
107 and  $\sim+160$  ppm assigned to  $^{17}\text{O}$  nuclei in  $\text{CO}_3^{2-}$  environments (Morizet et al. 2017). The peak  
108 at  $\sim+100$  ppm is less apparent in Mg-bearing compositions (HK and XE) whereas it is  
109 prominent in Mg-free Ca-rich RB8E composition consistent with the peak assignment to  $\text{Ca}^{2+}$   
110 NBO (Thompson and Stebbins 2011). The presence of  $\text{Mg}^{2+}$  surrounded by oxygen atoms  
111 units is proposed at  $\sim+50$ -70 ppm (Allwardt and Stebbins 2004) but not clearly visible here  
112 due to strong overlap with the BO-(Si,Al) signal at  $\sim+50$  ppm.  
113 The selective heteronuclear  $\{X\}$ - $^{17}\text{O}$  J-HMQC NMR pulse sequence probes local  
114 environments of oxygen atoms bound to X atoms. Hence, it should be pointed out that

115 chemical bonds involving nuclei other than the considered one (X) will not contribute to the  
116  $^{17}\text{O}$  NMR signal in the  $\{\text{X}\}$ - $^{17}\text{O}$  J-HMQC spectrum. Serendipitously, the  $\{^{13}\text{C}\}$ - $^{17}\text{O}$  J-HMQC  
117 spectra show a single line located at  $\sim+160$  ppm confirming that this peak is associated with  
118  $\text{CO}_3^{2-}$  molecular groups. More importantly, the absence of signal at  $\sim+50$  or  $+100$  ppm  
119 indicates that the  $\text{CO}_3^{2-}$  is connected neither to an available NBO nor to a BO. This is also  
120 confirmed by the  $\{^{29}\text{Si}\}$ - $^{17}\text{O}$  J-HMQC spectra, which do not exhibit a signal at  $+160$  ppm but  
121 only at  $+50$  and  $+100$  ppm; this is consistent with  $^{17}\text{O}$  atoms in BO and NBO configuration,  
122 respectively. The absence of common  $^{17}\text{O}$  signals in the  $\{^{29}\text{Si}\}$ - $^{17}\text{O}$  J-HMQC and  $\{^{13}\text{C}\}$ - $^{17}\text{O}$  J-  
123 HMQC spectra shows that there is no oxygen atom simultaneously bound to silicon and  
124 carbon atoms (within the detection level of  $\sim 5\%$ ) thereby precluding the existence of T- $\text{CO}_3^{2-}$ -  
125 T and NBO- $\text{CO}_3^{2-}$  carbonate units. This  $\text{CO}_2$ -dissolution mechanism has been proposed on the  
126 basis of FTIR results (Brooker et al. 2001), inferred from Molecular Dynamic simulations  
127 (Vuilleumier et al. 2015) and indirectly suggested from the change in the network structure  
128 upon  $\text{CO}_2$ -dissolution (Mysen et al. 2011; Mysen 2012; Moussallam et al. 2016). Our results  
129 are consistent with the MD results from Vuilleumier et al. (2015) suggesting that FIC  
130 represents 75% of the dissolved  $\text{CO}_3^{2-}$  molecular groups and 25% corresponding to network  
131 carbonate units (T- $\text{CO}_3^{2-}$ -T with T = Si or Al; Brooker et al. 2001). In the FIC  $\text{M}^{n+} \cdot \text{CO}_3^{2-}$ ,  
132  $\text{M}^{n+}$  is a charge balancing cation which can be  $\text{Mg}^{2+}$ ,  $\text{Ca}^{2+}$  and  $\text{Na}^+$  to a lower extent ( $\text{Na}_2\text{O}$  is  
133  $\sim 5$  wt.%) for the currently investigated compositions. Although, Morizet et al. (2017) showed  
134 that  $\text{CO}_3^{2-}$  groups dissolve preferentially in the vicinity of  $\text{Ca}^{2+}$  cations, we do not exclude the  
135 possibility for  $\text{Mg}^{2+} \cdot \text{CO}_3^{2-}$  being formed considering that  $\text{Mg}^{2+}$  could play a role comparable  
136 to  $\text{Ca}^{2+}$  (Cormier and Cuello 2013).

137 At this point, we wish to raise the level of confidence in the above discussion. Indeed, one  
138 could argue that the  $^{17}\text{O}$  signal from Si-O-C linkages could be absent from the  $\{^{29}\text{Si}\}$ - $^{17}\text{O}$  J-  
139 HMQC spectrum if the associated  $J(^{29}\text{Si}-^{17}\text{O})$  coupling value strongly differs from those

140 occurring for  $^{29}\text{Si}$ - $^{17}\text{O}(\text{BO})$  or  $^{29}\text{Si}$ - $^{17}\text{O}(\text{NBO})$  linkages. A simple way to rule out this  
141 possibility is to show that the full  $^{17}\text{O}$  spectrum can be totally reconstructed as the sum of the  
142 3 selective  $\{\text{X}\}$ - $^{17}\text{O}$  J-HMQC spectra. The reconstructions of the  $^{17}\text{O}$  MAS NMR spectra from  
143 the deconvolution of the  $\{\text{X}\}$ - $^{17}\text{O}$  J-HMQC spectra are shown in Figure 2 for three  $^{17}\text{O}$  MAS  
144 NMR spectra: Mg-free RB8E-12 (Figure 2A) and Mg-bearing XE-2 and HK-1 (Figure 2B and  
145 C). The deconvolution procedure was conducted as follows: each  $\{\text{X}\}$ - $^{17}\text{O}$  J-HMQC NMR  
146 spectrum was fitted with Gaussian lines; one line for the  $\{^{13}\text{C}\}$ - $^{17}\text{O}$  J-HMQC, one line for the  
147  $\{^{27}\text{Al}\}$ - $^{17}\text{O}$  J-HMQC and two lines for the  $\{^{29}\text{Si}\}$ - $^{17}\text{O}$  J-HMQC corresponding to the BO-Si  
148 and NBO-Si environments, respectively. The parameters obtained are reported in Table 1.  
149 Since the  $\{^{27}\text{Al}\}$ - $^{17}\text{O}$  J-HMQC spectrum was not acquired for all the samples due to the  
150 requirement of very long acquisition times, we used the  $\delta_{\text{iso}}$  and FWHM from the XE-2  
151 deconvolution for HK spectra; and the average  $\delta_{\text{iso}}$  and FWHM obtained from RB8E-12 and  
152 RB8E-13 for RB8E-7 spectrum. In Figure 2A, we show that the performed deconvolution  
153 adequately reproduces the  $^{17}\text{O}$  MAS NMR spectrum for the Mg-free RB8E-12 sample. The  
154 high carbon content of this sample excludes the possibility of a lack of  $^{17}\text{O}$  signal of  
155 significant intensity in the  $\{^{29}\text{Si}\}$ - $^{17}\text{O}$  J-HMQC spectrum. For Mg-bearing compositions, the  
156  $^{17}\text{O}$  MAS NMR spectra are not perfectly reproduced by the deconvolution. Regardless of the  
157 glass composition (XE-2 and HK), the residuals of the simulation exhibit a signal located at  
158  $\sim +70$  ppm not accounted for. Considering that this residual NMR signal is only observed in  
159 Mg-bearing glass composition, the signal could be attributed to oxygen atoms in  $\text{MgO}_x$   
160 configuration. This assignment would be consistent with the results of Hung et al. (2016)  
161 which identified  $^{17}\text{O}$  resonance for  $\text{MgO}_x$  oxygens in Ca/Mg orthosilicate glasses at +60 ppm.  
162 Considering that the NMR signal of the  $\text{CO}_3^{2-}$  environments is reproduced adequately by a  
163 single line at  $\sim +160$  ppm, the majority of the  $\text{CO}_3^{2-}$  groups are FIC in the investigated glass  
164 compositions.



165 IMPLICATION FOR CARBONATE – SILICATE LIQUID IMMISCIBILITY

166 Numerous implications arise from the present results; however we only focus on two of them:  
167 1) the immiscibility between carbonate and silicate liquids and 2) the impact of FIC on the  
168 carbonated melt transport properties. It is reasonable to consider that the  $M^{n+}..CO_3^{2-}$  FIC  
169 constitutes a carbonate subnetwork intimately mixed within a silicate subnetwork. For  
170 instance, Kubicki and Stolper (1995) showed that the molecular energy involved for ion pairs  
171 complexes (similar to FIC  $M^{n+}..CO_3^{2-}$ ) is low as compared to any other type of carbonates  
172 dissolved in silicate melt. Therefore, the energy barrier to dissociate the carbonate subnetwork  
173 from the silicate subnetwork is lower in the case of FIC.

174 Network-modifying cations have varying coordination numbers in a silicate melt (e.g. 5 to 8  
175 for  $Ca^{2+}$ ; Cormier and Cuello 2013). Upon  $CO_2$  dissolution, the network-modifying cation  
176 will share less of its positive charges to the silicate network in order to compensate the  
177 negative charges of the  $CO_3^{2-}$  groups; resulting in a network-modifying cation that is less  
178 connected to the silicate network. In particular, Vuilleumier et al. (2014) showed that the Ca-  
179 O distance in molten  $CaCO_3$  is on average 2.35 Å, suggesting that  $Ca^{2+}$  is more closely  
180 connected to the carbonate subnetwork than to the silicate subnetwork. Consequently, we  
181 believe that the presence of FIC  $M^{n+}..CO_3^{2-}$  could be viewed as a possible precursor to  
182 immiscibility. For instance, removal of the carbonate network from the silicate network is a  
183 proposed mechanism to form calciocarbonatite from a melilitite parental melt (Guzmics et al.  
184 2015).

185 We suggest that this immiscibility could also proceed from kimberlite owing to the fact that  
186 FIC groups are observed in the investigated HK composition analogous to kimberlite melt.  
187 However, the molecular configuration  $M^{n+}..CO_3^{2-}$  FIC poses the problem of the way  $CO_2$   
188 degasses from depolymerized silicate melts. The  $CO_2$  migration into the fluid phase imposes a

189 molecular structure reconfiguration to dissociate the  $M^{n+}..CO_3^{2-}$  groups and causes the  
190 network-modifying cation to remain in the silicate melt, thus depolymerizing the silicate  
191 network structure. This difficulty could explain the absence of degassing in kimberlitic melt  
192 upon decompression as witnessed by Moussallam et al. (2015).

193 Finally, it turns out that the identified  $CO_2$ -dissolution mechanism can also affect the physical  
194 properties of carbonated melts (e.g. magma transport and electrical conductivity).

195 Interconnection between FIC molecular groups could explain the high electrical conductivity  
196 observed in  $CO_2$ -bearing silicate melt (Sifré et al. 2014). There is an intimate mixture between  
197 a carbonate subnetwork having an extremely low viscosity and a silicate subnetwork with a  
198 higher viscosity (Morizet et al. *in press*). Through immiscibility, the carbonate liquid will  
199 migrate towards the surface due to its low viscosity and density (Vuilleumier et al. 2014),  
200 whereas the silicate liquid, which becomes enriched in  $SiO_2$ , is stalled at depth due to the  
201 increased viscosity (Giordano et al. 2008). Therefore, the direct proof of the existence of FIC  
202 gives legitimacy to the development and application of the immiscibility theory in a wide  
203 range of processes taking place in the Earth's interior.

204 *Acknowledgement: The authors thank the ANR agency which financed the current work*  
205 *through the ANR-2010-BLAN-621 "Electrolith". The authors would like to thank the*  
206 *European Research Council who partly funded this work through the ERC project grant*  
207 *number 279790. The authors thank the University of Orléans, the University of Nantes and*  
208 *the CNRS for their access to analytical facilities. The authors thank the TGIR RMN Très*  
209 *Hauts Champs for accessing to the high field NMR spectrometer.*

210

## 211 References

212 Allwardt, J.R., and Stebbins, J.F. (2004) Ca-Mg and K-Mg mixing around non-bridging O  
213 atoms in silicate glasses: an investigation using  $^{17}O$  MAS and 3QMAS NMR. American  
214 Mineralogist 89, 777–784.

- 215 Allwardt, J.R., Lee, S.K., and Stebbins, J.F. (2003) Ca-Mg and K-Mg mixing around non-  
216 bridging O atoms in silicate glasses: An investigation using  $^{17}\text{O}$  MAS and 3QMAS NMR.  
217 American Mineralogist 89, 777-784.
- 218 Amoureux, J.P., Trebosc, J., Wiench, J., and Pruski, M. (2007) HMQC and refocused-INEPT  
219 experiments involving half-integer quadrupolar nuclei in solids. Journal of Magnetic  
220 Resonance 184, 1-14. Bosshard-Stadlin, S.A., Mattsson, H.B., and Keller, J. (2014) Magma  
221 mixing and forced exsolution of  $\text{CO}_2$  during the explosive 2007–2008 eruption of Oldoinyo  
222 Lengai (Tanzania). Journal of Volcanology and Geothermal Research 285, 229–246.
- 223 Brooker, R.A., and Kjarsgaard, B.A. (2011) Silicate–carbonate liquid immiscibility and phase  
224 relations in the system  $\text{SiO}_2\text{--Na}_2\text{O--Al}_2\text{O}_3\text{--CaO--CO}_2$  at 0.1–2.5 GPa with applications to  
225 carbonatite genesis. Journal of Petrology 52, 1281–1305.
- 226 Brooker, R.A., Kohn, S.C., Holloway, J.R., and McMillan, P.F. (2001) Structural controls on  
227 the solubility of  $\text{CO}_2$  in silicate melts. Part II: IR characteristics of carbonate groups in silicate  
228 glasses. Chemical Geology 174, 241–254.
- 229 Brooker, R.A., Sparks, R.S.J., Kavanagh, J.L., and Field, M. (2011) The volatile content of  
230 hypabyssal kimberlite magmas: some constraints from experiments on natural rock  
231 compositions. Bulletin of Volcanology, 73, 959–981.
- 232 Cormier, L., and Cuello, G.J. (2013) Structural investigation of glasses along the  $\text{MgSiO}_3\text{--}$   
233  $\text{CaSiO}_3$  join: Diffraction studies. Geochimica et Cosmochimica Acta 122, 498-510.
- 234 Eggler, D.H. (1978) The effect of  $\text{CO}_2$  upon partial melting of peridotite in the system  $\text{Na}_2\text{O--}$   
235  $\text{CaO--Al}_2\text{O}_3\text{--MgO--SiO}_2\text{--CO}_2$  to 35kb, with an analysis of melting in a peridotite- $\text{H}_2\text{O--CO}_2$   
236 system. American Journal of Science 278, 305–343.

- 237 Giordano, D., Russell, J.K., and Dingwell, D.B. (2008) Viscosity of magmatic liquids: a  
238 model. *Earth Planetary Science Letters* 271, 123–134.
- 239 Guillot, B., and Sator, N. (2011) Carbon dioxide in silicate melts: A molecular dynamics  
240 simulation study. *Geochimica et Cosmochimica Acta* 75, 1829-1857.
- 241 Guzmics, T., Zajacz, Z., Mitchell, R.H., Szabo, C., and Wälle, M. (2015) The role of liquid–  
242 liquid immiscibility and crystal fractionation in the genesis of carbonatite magmas: insights  
243 from Kerimasi melt inclusions. *Contributions to Mineralogy and Petrology* 169, 17-35.
- 244 Hung, I., Gan, Z., Gor'kov, P.L., Kaseman, D.C., Sen, S., LaComb, M., and Stebbins, J.F.  
245 (2016) Detection of “free” oxide ions in low-silica Ca/Mg silicate glasses: Results from  $^{17}\text{O}$   
246  $\rightarrow$   $^{29}\text{Si}$  HETCOR NMR. *Journal of Non-Crystalline Solids* 445-446, 1-6.
- 247 Keller, J., Zaitsev, A.N., and Wiedenmann, D. (2006) Primary magmas at Oldoinyo Lengai:  
248 the role of olivine melilitites. *Lithos* 91,150–172
- 249 Keeler, J. (2010) *Understanding NMR Spectroscopy*. The Atrium, Chichester, West Sussex,  
250 PO19 8SQ, United Kingdom, John Wiley & Sons Ltd., 526p.
- 251 Kelsey, K.E., Allwardt, J.R., and Stebbins, J.F. (2008) Ca-Mg mixing in aluminosilicate  
252 glasses: An investigation using the  $^{17}\text{O}$  MAS and 3QMAS and  $^{27}\text{Al}$  MAS NMR. *Journal of*  
253 *Non-Crystalline Solids* 354, 4644–4653.
- 254 Kjarsgaard, B.A., Pearson, D.G., Tappe, S., Nowell, G.M., and Dowall, D.P. (2009)  
255 Geochemistry of hypabyssal kimberlites from Lac de Gras, Canada: Comparisons to a global  
256 database and applications to the parent magma problem. *Lithos* 1125, 236-248.

- 257 Kubicki, J.D., and Stolper, E.M. (1995) Structural roles of CO<sub>2</sub> and [CO<sub>3</sub>]<sup>2-</sup> in fully  
258 polymerized sodium aluminosilicate melts and glasses. *Geochimica et Cosmochimica Acta*  
259 59, 683-698.
- 260 Le Bas, M.J. (1987) Nephelinites and carbonatites. Geological Society Special Publication 30,  
261 53-83.
- 262 Lee, S.K., and Stebbins, J.F. (2003) Nature of cation mixing and ordering in Na-Ca silicate  
263 glasses and melts. *Journal of Physical Chemistry B* 107, 3141–3148.
- 264 Mitchell, R.H. (2005) Carbonatites and carbonatites and carbonatites. *Canadian Mineralogist*  
265 43, 2049–2068.
- 266 Morizet, Y., Brooker, R.A., Iacono-Marziano, G., and Kjarsgaard, B. (2013) Quantification of  
267 CO<sub>2</sub> dissolved in silicate glasses of various compositions with Micro-Raman spectroscopy.  
268 *American Mineralogist* 98, 1788–1802.
- 269 Morizet, Y., Paris, M., Gaillard, F., and Scaillet, B. (2014) Carbon dioxide in silica-  
270 undersaturated melt. Part I: the effect of mixed alkalis (K and Na) on CO<sub>2</sub> solubility and  
271 speciation. *Geochimica et Cosmochimica Acta* 141, 45–61.
- 272 Morizet, Y., Paris, M., Sifré, D., Di Carlo, I., and Gaillard, F. (2017) The effect of Mg  
273 concentration in silicate glasses on CO<sub>2</sub> solubility and solution mechanism: Implication for  
274 natural magmatic systems. *Geochimica et Cosmochimica Acta* 198, 115-130.
- 275 Morizet, Y., Paris, M., Sifré, D., Di Carlo, I., Ory, S., and Gaillard, F. (*in press*) Towards the  
276 reconciliation of viscosity change and CO<sub>2</sub>-induced polymerization in silicate melts. *Chemical*  
277 *Geology* DOI: [10.1016/j.chemgeo.2017.03.028](https://doi.org/10.1016/j.chemgeo.2017.03.028).

- 278 Moussallam, Y., Morizet, Y., Massuyeau, M., Laumonier, M., and Gaillard, F. (2015) CO<sub>2</sub>  
279 solubility in kimberlite melts. *Chemical Geology* 418, 198-205.
- 280 Moussallam, Y., Florian, P., Corradini, D., Morizet, Y., Sator, N., Vuilleumier, R., Guillot,  
281 B., Iacono-Marziano, G., Schmidt, B.C., and Gaillard, F. (2016) The molecular structure of  
282 melts along the carbonatite–kimberlite–basalt compositional joint: CO<sub>2</sub> and polymerization.  
283 *Earth Planetary Science Letters* 434, 129-140.
- 284 Mysen, B.O. (2012) Silicate-COH melt and fluid structure, their physicochemical properties,  
285 and partitioning of nominally refractory oxides between melts and fluids. *Lithos* 148, 228-  
286 246.
- 287 Mysen, B.O., and Virgo, D. (1980) Solubility mechanisms of carbon dioxide in silicate melts;  
288 a Raman spectroscopic study. *American Mineralogist* 65, 885–899.
- 289 Mysen, B.O., Eggler, D.H., Setiz, M.G., and Holloway, J.R. (1976) Carbon dioxide in silicate  
290 melt and crystals: Part I solubility measurements. *American Journal of Science* 276, 455-479.
- 291 Mysen, B.O., Kumamoto, K., Cody, G.D., and Fogel, M.L. (2011) Solubility and solution  
292 mechanisms of C-O-H volatiles in silicate melt with variable redox conditions and melt  
293 composition at upper mantle temperatures and pressures. *Geochimica et Cosmochimica Acta*  
294 75, 6183–6199.
- 295 Russell, J.K., Porritt, L.A., Lavallée, Y., and Dingwell, D.B. (2012) Kimberlite ascent by  
296 assimilation-fuelled buoyancy. *Nature* 481, 352–356.
- 297 Sifré, D., Gardès, E., Massuyeau, M., Hashim, L., Hier-Majumder, S., and Gaillard, F. (2014)  
298 Electrical conductivity during incipient melting in the oceanic low-velocity zone. *Nature* 509,  
299 81–87.

300 Spera, F.J., and Bergman, S.C. (1980) Carbon dioxide in igneous petrogenesis: I. Aspects of  
301 the dissolution of CO<sub>2</sub> in silicate liquids. *Contributions to Mineralogy and Petrology* 74, 55-  
302 66.

303 Stebbins, J.F., Lee, S.K., and Oglesby, J.V. (1999) Al-O-Al oxygen sites in crystalline  
304 aluminates and aluminosilicate glasses: high-resolution oxygen-17 NMR results. *American*  
305 *Mineralogist*, 84, 983–986.

306 Thompson, L.M., and Stebbins, J.F. (2011) Non-bridging oxygen and high-coordinated  
307 aluminum in metaluminous and peraluminous calcium and potassium aluminosilicate glasses:  
308 High-resolution <sup>17</sup>O and <sup>27</sup>Al MAS NMR results. *American Mineralogist* 96, 841–853.

309 Vuilleumier, R., Seitsonen, A., Sator, N., and Guillot, B. (2014) Structure, equation of state  
310 and transport properties of molten calcium carbonate (CaCO<sub>3</sub>) by atomistic simulations.  
311 *Geochimica et Cosmochimica Acta* 141, 547-566.

312 Vuilleumier, R., Seitsonen, A.P., Sator, N., and Guillot, N. (2015) Carbon dioxide in silicate  
313 melts at upper mantle conditions: Insights from atomistic simulations. *Chemical Geology* 418,  
314 77–88.

315 Xue, X., and Kanzaki, M. (2013) Carbonate speciation in depolymerized silicate melts  
316 (glasses): New evidence from ab initio calculations and <sup>13</sup>C MAS and static NMR  
317 measurements. *Mineralogical Magazine* 77, 2533.

318 **Figure caption:**

319 Figure 1. <sup>17</sup>O MAS and {<sup>13</sup>C}- {<sup>27</sup>Al}- {<sup>29</sup>Si}-<sup>17</sup>O J-HMQC NMR spectra of CO<sub>2</sub>-  
320 bearing silicate glasses: XE-2 (A), HK-1 (B), HK-M (C) and RB8E-12 (D). Three oxygen  
321 environments are identified with MAS spectra: FIC M<sup>n+</sup>..CO<sub>3</sub><sup>2-</sup>, Ca<sup>2+</sup> NBO-Si and BO-(Si,Al).  
322 The NMR spectra for the other synthesized glasses can be found in Supplementary material.

323           Figure 2.  $^{17}\text{O}$  MAS spectrum deconvolution obtained from Gaussian lines derived  
324 from {X}- $^{17}\text{O}$  J-HMQC spectra. The deconvolution of the  $^{17}\text{O}$  NMR spectra for the other  
325 synthesized glasses can be found in Supplementary material.



Revision 1

Table 1: Experimental conditions, chemical compositions of the investigated synthetic Fe-free silicate glasses.

Sample	HK-1	HK-2	HK-M	RB8E-7	RB8E-12	RB8E-13	XE-2	Natural Kimberlite <sup>§</sup>	Natural Melilitite <sup>§</sup>
Pressure (GPa)	1.5	0.5	1.5	0.5	1.0	1.0	1.5		
Glass chemical composition in wt.%									
SiO <sub>2</sub>	40.2	40.1	31.8	33.3	30.3	30.1	40.6	30.4	36.5
Al <sub>2</sub> O <sub>3</sub>	4.3	4.4	3.5	8.7	8.1	8.6	14.8	2.3	7.7
MgO	21.9	21.3	21.9	0.0	0.1	0.2	12.6	29.7	11.8
CaO	22.0	22.3	22.0	41.8	39.8	36.0	17.8	9.6	14.2
Na <sub>2</sub> O	4.5	4.5	3.5	5.7	4.8	5.0	4.8	0.1	4.3
CO <sub>2</sub> <sup>*</sup>	7.1	2.9	13.2	6.5	12.6	7.7	4.2	6.40	0.52
H <sub>2</sub> O <sup>†</sup>	0.8	1.0	1.3	0.7	1.5	1.3	1.0	7.10	1.06
NBO/T from stoichiometry <sup>‡</sup>	2.6	2.5	3.2	2.1	2.2	1.9	1.2	3.60	1.66
NMR parameters <sup>  </sup>									
Free Ca <sup>2+</sup> ..CO <sub>3</sub> <sup>2-</sup>									
δ <sub>iso</sub>	154.2	157.3	155.7	164.9	164.6	166.0	157.8		
FWHM	42.0	41.3	44.2	34.7	30.7	33.6	45.3		
BO-Si									
δ <sub>iso</sub>	54.4	57.4	55.2	61.0	51.6	53.4	48.7		
FWHM	24.4	29.3	24.3	23.3	24.3	22.3	25.5		
BO-Al									
δ <sub>iso</sub>	42.5	42.5	42.5	47.8	45.5	47.5	42.5		
FWHM	25.8	25.8	25.8	25.6	25.7	25.5	25.8		
NBO-Si									
δ <sub>iso</sub>	95.9	96.7	96.0	106.5	106.8	106.2	99.3		
FWHM	31.4	33.1	23.7	24.6	25.2	24.0	47.1		

<sup>\*</sup> The glass CO<sub>2</sub> content has been determined using Raman spectroscopy and the method described in Morizet et al. (2013). With the derived CO<sub>3</sub>/HF ratio obtained from the deconvolution of the Raman spectra (see Supplementary material), it is possible to determine the CO<sub>2</sub> content using the linear relationship wt.% CO<sub>2</sub> = 13.5 x CO<sub>3</sub>/HF. The typical error on the CO<sub>2</sub> content using Raman method is 10% in relative to the value.

<sup>†</sup> The H<sub>2</sub>O content was determined by FTIR spectroscopy on a doubly polished glass plate. Contribution for OH<sup>-</sup> and H<sub>2</sub>O<sup>mol</sup> vibrational peaks at 4500 and 5200 cm<sup>-1</sup> were summed to obtain the H<sub>2</sub>O<sup>tot</sup>. The error does not exceed ±0.2 wt.% H<sub>2</sub>O and corresponds to the standard deviation obtained on the replicated measurements.

<sup>‡</sup> The NBO/T describing the average polymerization was calculated on a stoichiometric basis using the chemical composition measured by EPMA.

<sup>§</sup> An average typical natural composition of kimberlite and melilitite were obtained from Kjarsgaard et al. (2009) and Keller et al. (2006), respectively. Additional oxides (TiO<sub>2</sub>, FeO and K<sub>2</sub>O for the most important) have not been reported but are nominally present: ~0.4 wt.% for TiO<sub>2</sub>, ~10.0 wt.% FeO and ~2.0 for K<sub>2</sub>O.

Figure 1




Figure 2

